CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-8548

QC ABSTRACT

ME OF WORK: Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.

O	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Fines by Air permeability method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness i.e Autoclave Method	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		Reflects tes.	One Test		1	1
6	Precast (150mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	PCC M20	Compressive Strength(7days and 28days)	6 set 100+150cum	122.16	12	12

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID : CP-2020-02-01-01 **Date: 14-11-19**

Project Name : Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.

Agency : Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010

Customer's Reference : BBMP/EE/BTP/WO/133/2019-20

Date of Receipt : 11-11-19

Sample Type : Birla Super 53grade

Reference to BIS codes : IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,
IS 4031 (Part 1,2 3,4,5, 6,11).1988
IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4
IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5
IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6
IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5
IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5
IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6

Date of test : 12-11-19

Environmental Conditions during test : Temperature: 26°C
Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.1	–
2	Finess by Air permeablity method (m^2/kg,Min)	284.5	225m^2/kg, Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	28%	Not specified
5	Initial Setting time	155 minutes	Not less than 30 minutes
6	Final Setting time	260 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2mm	Not more than 10 mm

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-02-01-01** **Date: 10-12-19**
Project Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
Agency	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
Date of Receipt	:	11-11-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	12-11-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-02-01-01** **Date: 14-11-19**
Project Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
Agency	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
Customer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
Date of Receipt	:	11-11-19
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	11-11-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	244	244	1.6	98.4	90-100
3	20 mm	5432	5676	37.8	62.2	30-70
4	10 mm	4332	10008	66.7	33.3	10-35
5	4.75 mm	4654	14662	97.7	2.3	0-5
6	Pan	338	15000	100.0	0	---

CIVIL PRO Sig. Dept. BANGALORE

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-02-01-01** **Date: 14-11-19**

PHYSICAL PROPERTIES

SLno	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.8	
3	Specific Gravity	2.68	_
4	Bulk Density(Loose) (Kg/l)	1.48	_
5	Bulk Density(Compacted) (Kg/l)	1.52	_
6	Water Absorption(%)	0.22	_

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-02-01-01**	**Date: 13-11-19**
Project Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.	
Agency	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010	
Customer Reference	:	BBMP/EE/BTP/WO/133/2019-20	
Date of Receipt	:	11-11-19	
Sample Type/ Size	:	20mm down size coarse aggregate	
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties	
Date of test	:	11-11-19	

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	245	245	4.9	95.1	90-100
3	10 mm	2560	2805	56.1	43.9	25-55
4	4.75 mm	2033	4838	96.8	3.2	0-10
5	Pan	162	5000	100	0	–

CIVIL PRO Sig. D.t. BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-02-01-01** **Date: 13-11-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.6	
3	Specific Gravity	2.66	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	24.5	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.8	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 13-11-19

ab ID	:	**CP-2020-02-01-01**
roject Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
gency	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
stomer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
te of Receipt	:	11-11-19
mple Type	:	Fine Aggregate
ference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids, Water Absorption
te of test	:	11-11-19
tal weight taken	:	1000 grams

no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
	10 mm	0	0	0.0	100.0	100	100	100	100
	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
	Pan	80	1000	100.0	0.0	—	—	—	—

lt :The tested Sample Conforms to Grading Zone II

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

CIVIL PRO BANGALORE

Scanned by CamScanner

TEST REPORT OF FINE AGGREGATE

ab ID : CP-2020-02-01-01 Date: 13-11-19

HYSICAL PROPERTIES

.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	_
2	Specific Gravity	2.59	_
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST RESULTS OF STEEL

b ID	:	CP-2020-02-01-01 **Date: 16-11-19**
ject Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
ency	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
stomer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
te of Receipt	:	15-11-19
nple Type	:	Sunvik
erence to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
te of test:	:	15-11-19

No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	21.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory
4	Sunvik	Fe500	16	1.581	572	674	19.0%	Satisfactory	Satisfactory

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
End of Report

Scanned by CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/11/2019

ID	:	CP-2020-02-01-01
ect Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
ıcy	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
omer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
of Receipt	:	20-11-19
omer ID	:	Drain Bottom Slab Concrete
ple Type /Size	:	150X150X150 mm
ple grade/Age	:	M20 / 7 Days Compressive Strength
rence to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
of test	:	25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	151.86 X 151.80 X 149.46	23053	8.715	415.2	18.0	18.3
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	149.49 X 150.60 X 151.42	22512	8.172	410.5	18.2	
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	149.60 X 150.26 X 149.79	22480	8.589	416.4	18.5	

ಸಹಾಯಕ ಕಾರ್ಯ ನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/12/2019

ID	:	CP-2020-02-01-01
ect Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
ncy	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
tomer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
of Receipt	:	20-11-19
tomer ID	:	Drain Bottom Slab Concrete
ple Type /Size	:	150X150X150 mm
ple grade/Age	:	M20 / 28 Days Compressive Strength
erence to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
e of test	:	16/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	151.34 X 150.48 X 150.09	22773	8.276	532.5	23.4	23.2
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	150.70 X 150.05 X 151.10	22613	8.865	505.4	22.3	
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	150.68 X 150.09 X 150.25	22617	8.119	540.8	23.9	

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/11/2019

D : CP-2020-02-01-01

ct Name : Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.

cy : Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010

mer's Reference : BBMP/EE/BTP/WO/133/2019-20

of Receipt : 20-11-19

mer ID : Drain Bottom Slab Concrete

le Type /Size : 150X150X150 mm

le grade/Age : M20 / 7 Days Compressive Strength

rence to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

of test : 25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	151.59 X 149.49 X 150.12	22661	8.715	428.8	18.9	18.7
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	151.05 X 151.73 X 150.23	22919	8.172	418.6	18.3	
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	149.29 X 149.44 X 149.37	22309	8.589	418.9	18.8	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-26

CIVIL PRO BANGALORE Sig. Dt.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/11/2019

ID	:	**CP-2020-02-01-01**
ct Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
cy	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
omer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
of Receipt	:	20-11-19
omer ID	:	Drain Bottom Slab Concrete
ple Type /Size	:	150X150X150 mm
ple grade/Age	:	M20 / 7 Days Compressive Strength
rence to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
of test	:	25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	150.96 X 151.50 X 149.32	22871	8.715	426.6	18.7	18.5
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	149.95 X 149.51 X 151.73	22418	8.172	414.2	18.5	
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	149.84 X 150.05 X 151.56	22484	8.589	415.6	18.5	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-02-01-01 **Date: 16/12/2019**

Name : Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010

er's Reference : BBMP/EE/BTP/WO/133/2019-20

Receipt : 20-11-19

ıer ID : Drain Bottom Slab Concrete

Type /Size : 150X150X150 mm

grade/Age : M20 / 28 Days Compressive Strength

nce to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

f test : 16/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	150.78 X 150.83 X 150.47	22742	8.276	533.2	23.4	23.1
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	150.40 X 150.84 X 151.91	22686	8.865	503.0	22.2	
Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	149.29 X 151.28 X 150.90	22584	8.119	535.6	23.7	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

D : CP-2020-02-01-01

Date: 25/11/2019

ct Name : Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.

cy : Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010

mer's Reference : BBMP/EE/BTP/WO/133/2019-20

of Receipt : 20-11-19

mer ID : Drain Bottom Slab Concrete

le Type /Size : 150X150X150 mm

le grade/Age : M20 / 7 Days Compressive Strength

ence to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

of test : 25/11/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	151.49 X 151.20 X 150.81	22905	8.715	425.1	18.6	18.5
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	150.83 X 150.25 X 149.17	22663	8.172	420.9	18.6	
Drain Bottom Slab Concrete	M20	18/11/2019	25/11/2019	151.24 X 149.84 X 150.35	22662	8.589	417.2	18.4	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

ID	:	CP-2020-02-01-01 **Date: 16/12/2019**
ect Name	:	Improvements to CC Roads and Drain at Chokkanahalli in Ward No.05.
ncy	:	Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560010
tomer's Reference	:	BBMP/EE/BTP/WO/133/2019-20
e of Receipt	:	20-11-19
tomer ID	:	Drain Bottom Slab Concrete
ple Type /Size	:	150X150X150 mm
ple grade/Age	:	M20 / 28 Days Compressive Strength
erence to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
e of test	:	16/12/2019

	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
	Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	150.56 X 150.44 X 151.42	22650	8.276	542.5	23.9	23.5
	Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	149.91 X 149.80 X 149.94	22457	8.865	509.3	22.7	
	Drain Bottom Slab Concrete	M20	18/11/2019	16/12/2019	149.72 X 151.41 X 151.35	22669	8.119	543.5	24.0	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by CamScanner